

# i.d™ Pearl Finish

Page 1 of 2  
Resource Code 1185 - Line  
July 2003

## DESCRIPTION

- Wattyl i.d™ Pearl Finish is a soft pearlescent finish, which captures the rich lustre of natural pearl, leaving an effect that absorbs yet reflects light.

## PRINCIPAL CHARACTERISTICS

- Suitable for interior use only.
- A natural finish with many variations, i.d™ Pearl Finish will cast a unique finish to your wall.

## COLOURS AND GLOSS

- Refer to the appropriate i.d™ Specialty Finishes Colour Card.
- Satin

## BASIC DATA

- **Surface Dry** One (1) hour.
- **Recoat** Four (4) hours.
- **Fully Cured** Seven (7) days.  
All figures are quoted at 25°C and 50% relative humidity. Drying will take longer at lower temperatures or higher relative humidity.
- **Coverage per coat** 18 M<sup>2</sup>/L (depending on the surface porosity and method of application)
- **Wet Film Thickness** 56 microns
- **Dry Film Thickness** N/A
- **Thinning** Not required
- **Clean up** Thoroughly clean equipment with water.

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURE

- Suitable for feature walls, interior trims, architraves, cornices, picture rails and wood surfaces.
- Ensure the surface is clean and dry. All loose, peeling and flaking material must be removed prior to coating.
- Application **should not** be carried out if the air temperature or the substrate temperature is below 10°C or above 35°C. The temperature must not fall below 10°C during the drying process.
- Freshly applied material must be protected from steam and condensation for a minimum of forty eight (48) hours.
- For specific substrate preparation, see relevant specification sheets.

## INSTRUCTIONS FOR USE

- Stir contents thoroughly with a flat stirrer before and during use.
- Note: Depending on the i.d™ Pearl Finish colour chosen, a U1, U2, U3 or U4 tinted undercoat **is** required.
- **First Coat**  
Cut in around edges and corners first, using a brush.  
Using a 10mm nap roller apply the first coat in sections that span the height of the wall, ensuring that you roll as close to the edge as possible. Carefully lay off the paint in one direction from top to bottom of the wall to give an even finish. Try to avoid noticeable lines appearing in the finish on either side of the roller. Avoid stoppages during this process. Repeat until the whole wall is complete.
- **Second Coat\***  
**Random Bush Effect** – Using a 100mm or wider brush, apply a second coat in a criss-cross action randomly. Note, each brush stroke will show when dry.  
**Dragged Brush Effect** – Roll the second coat in a similar manner to the first. Whilst the paint is still wet use a dry wide brush, soft household broom or wallpaper brush and drag lightly in 1m wide vertical sections from ceiling to floor in straight lines. This creates a more even subtle finish.  
**Sponging Effect** – Sponge on the second coat using a slightly dampened sea sponge working in small sections

\* In some cases a third coat may be required.

### SAFETY DATA

- **Caution** Provide adequate ventilation during use.
- **Spills and Disposal** Do not allow spilt material to enter drains or other watercourses. Absorb spills with sand or other inert material. Unwanted paint should be kept in a sealed container, such as an empty paint can, and disposed of via special waste collection services. Check with your local Council regarding the disposal of empty paint containers.
- **M.S.D.S.** A Material Safety Data Sheet (M.S.D.S.) is available on request.
- **First Aid**
  - If swallowed **do not** induce vomiting. Give plenty of water to drink. Contact a doctor or the Poisons Information Centre. Phone 131126 (Australia).
  - If in eyes, hold eyes open and flood with water for at least 15 minutes. Contact a doctor if any irritation occurs.
  - If on skin remove contaminated clothing, wash skin thoroughly with soap and water or a proprietary skin cleanser. Do not use solvents.
  - If affected by inhalation remove person to fresh air. If breathing difficulties persist or occur later, contact a doctor.

### ADDITIONAL DATA

- Available in 500 ml, 1, and 4 litre containers.
- Containers must be secured and stored upright during transit.
- Containers must not be exposed to excessive heat or cold.
- Leave seven days after application of final coat before washing.
- When subject to steam or condensation, water based paints may develop a stain, which can be removed with a damp cloth. Avoid exposure to excessive steam or condensation for 48 hours after application of the final coat.
- For further information, contact the Wattyl Information Hotline. Phone 132101(Australia).

1. This information is provided with respect to the listed Wattyl products. Wattyl recommends that:  
(a) you review the Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS) before you use or handle the product; (b) the product be used only in accordance with the information provided by Wattyl; (c) the product be transported, stored and handled in accordance with the information on the MSDS and relevant TDS; and (d) you thoroughly test the product, using the recommended application method on a sample of intended substrate, before using the product.  
2. The information in this technical data sheet was prepared using information gathered during product development. While Wattyl endeavours to update this information and maintain the accuracy and currency of its contents, Wattyl cannot guarantee that the information provided is wholly comprehensive.  
3. Wattyl recommends that you conduct such additional investigations as may be necessary to satisfy yourself of the accuracy, currency and comprehensiveness of the information on which you rely in using and handling the product. If you require further information please contact your nearest Wattyl Office.  
4. To the full extent permitted by law, Wattyl's liability for breach of a condition or warranty implied into the contract for sale between Wattyl and you by law is limited at Wattyl's election to: (a) the replacement of the product; or (b) payment of the cost of replacing the product.